


AM 0/8-750 Coating

Client : Quality Control Argex
 0032/32.50.15.15

lab	Quality Control Argex 0032/32.50.15.15
Aggregate Size	0/8 mm
Certifications	EN 13055 : . (1/01/2004)

Essential char. - performance	Minimum	Average	Maximum	Declared	Standard
Particle Shape		Mix			EN 13055
Loose Bulk Density (+- 15% of declared value)	650	808 kg/m ³	850	750	EN 1097-3
Oven-Dried Particle Density (+- 15% of declared value)	1080	1325 kg/m ³	1380	1230	EN 1097-6 Filtermethod
Freezing & Thawing Resistance		2.3 %	3.3		NF P18-545
Volume Stability		0.22 %	0.50		EN 1367-8
Water Content (from silo)	0.0	13.7 %	14.0		EN 1097-5
Water Absorption 2h	6.00	7.67 %	12.00		EN 1097-6 Filtermethod
Water Absorption 30'	5.00	6.60 %	11.00		EN 1097-6 Filtermethod
Water Absorption 5'	4.00	5.82 %	10.00		EN 1097-6 Filtermethod
Active alkalines content (Na ₂ O eq.)		0.044 %			LPC 37
Alkali - reactivity (qualification)		No Reactive (NR)			FD P18-542
Chloride		0.005 %	0.010		EN 1744-1
Total Sulphur		0.28 %	0.55		EN 1744-1
Acid-Soluble Sulfate		0.107 %	0.500		EN 1744-1

Grading (EN 933-1)				
sieve (mm)	mini	% passing	maxi	Declared
0.000		0.0		
0.063		5.0		
0.125		9.5		
0.250		13		
0.500		17		
1.000		24		
2.000		40		
3.150		50		
4.000		57		
6.300		81		
8.000	90	98	100	
10.000		100		



WIL 11.05.2.205 (c) Arcade 1996,2020