



AR 4/10-550

Client : Quality Control Argex
0032/32.50.15.15

lab	Quality Control Argex 0032/32.50.15.15
Aggregate Size	4/10 mm
Certifications	EN 13055 : . (1/01/2004)

Essential char. - performance	Minimum	Average	Maximum	Declared	Standard
Particle Shape		Round			EN 13055
Crushing Resistance (T-2x30")	2.22	4.90 N/mm ²	8.05		EN 13055
Loose Bulk Density (+- 15% of declared value)	468	565 kg/m ³	632	550	EN 1097-3
Oven-Dried Particle Density (+- 15% of declared value)	819	1014 kg/m ³	1107	970	EN 1097-6 annex C
Freezing & Thawing Resistance		2.3 %	3.3		EN 1367-7
Los Angeles + Micro Deval (4-6.3)		NPD			EN 1097-1 & 2
Los-Angeles (4-6.3)		NPD			EN 1097-2
Polished Stone Value		NPD			EN 1097-8
Volume Stability		0.22 %	0.50		EN 1367-8
Water Content (from silo)	0.0	2.2 %	15.0		EN 1097-5
Water Absorption 5'	5.67	11.44 %	15.52		EN 1097-6 annex C
Water Absorption 1h	8.32	14.79 %	19.38		EN 1097-6 annex C
Water Absorption 24h	15.49	23.09 %	30.71		EN 1097-6 annex C
Alkali Silica Reactivity		NPD			EN 13055
Chloride		0.005 %	0.010		EN 1744-1
Cleanliness		Pass			EN 1744-1
Loss on Ignition		-0.18 %	0.50		EN 1744-1
Release Of Dangerous Substances		NPD			EN 13055
Reaction To Fire		Euroclass A1			EN 13501-1
Total Sulphur		0.33 %	0.55		EN 1744-1
Acid-Soluble Sulfate		0.055 %	0.500		EN 1744-1

Grading (EN 933-1)				
sieve (mm)	mini	% passing	maxi	Declared
0.000		0.0		
0.063		0.4		
2.000		1.3		
3.150		3.4		
4.000	0.0	7.8	15.0	
6.300		54		
8.000		91		
10.000	90	100	100	
12.500		100		

