

AG 0/2-580

Client : Quality Control Argex
 0032/32.50.15.15

lab	Quality Control Argex 0032/32.50.15.15
Aggregate Size	0/2 mm
Certifications	EN 13055 : NL BSB K73820 (1/01/2004)

Essential char. - performance	Minimum	Average	Maximum	Declared	Standard
Particle Shape		Crushed			EN 13055
Crushing Resistance (T-2x30")		NPD			EN 13055
Loose Bulk Density (+- 15% of declared value)	493	617 kg/m ³	667	580	EN 1097-3
Oven-Dried Particle Density (+- 15% of declared value)	888	1080 kg/m ³	1202	1045	EN 1097-6 annex D
Freezing & Thawing Resistance		NPD			EN 1367-7
Los Angeles + Micro Deval (4-6.3)		NPD			EN 1097-1 & 2
Los-Angeles (4-6.3)		NPD			EN 1097-2
Polished Stone Value		NPD			EN 1097-8
Volume Stability		NPD			EN 1367-8
Water Content (from silo)	0.0	1.8 %	15.0		EN 1097-5
Water Absorption 5'	30.10	33.36 %	33.80		EN 1097-6 annex D
Alkali Silica Reactivity		NPD			EN 13055
Chloride		0.005 %	0.010		EN 1744-1
Cleanliness		Pass			EN 1744-1
Release Of Dangerous Substances		NPD			EN 13055
Reaction To Fire		Euroclass A1			EN 13501-1
Total Sulphur		0.42 %	0.55		EN 1744-1
Acid-Soluble Sulfate		0.156 %	0.500		EN 1744-1

Grading (EN 933-1)				
sieve (mm)	mini	% passing	maxi	Declared
0.000		0.0		
0.063		16		
0.125		28		
0.250		40		
0.500		53		
1.000		70		
2.000	90	94	100	
3.150		100		

