

AG 1/5-390

Client : Quality Control Argex
 0032/32.50.15.15

lab	Quality Control Argex 0032/32.50.15.15
Aggregate Size	1/5 mm
Certifications	EN 13055 : NL BSB K73820 (1/01/2004)

Essential char. - performance	Minimum	Average	Maximum	Declared	Standard
Particle Shape		Crushed			EN 13055
Crushing Resistance (T-2x30")		NPD			EN 13055
Loose Bulk Density (+- 15% of declared value)	332	404 kg/m ³	449	390	EN 1097-3
Oven-Dried Particle Density (+- 15% of declared value)	663	844 kg/m ³	897	780	EN 1097-6 annex D
Freezing & Thawing Resistance		NPD			EN 1367-7
Los Angeles + Micro Deval (4-6.3)		NPD			EN 1097-1 & 2
Los-Angeles (4-6.3)		NPD			EN 1097-2
Polished Stone Value		NPD			EN 1097-8
Volume Stability		NPD			EN 1367-8
Water Content (from silo)	0.0	1.9 %	15.0		EN 1097-5
Water Absorption 5'	28.68	35.23 %	39.75		EN 1097-6 annex D
Alkali Silica Reactivity		NPD			EN 13055
Chloride		0.005 %	0.010		EN 1744-1
Cleanliness		Pass			EN 1744-1
Release Of Dangerous Substances		NPD			EN 13055
Reaction To Fire		Euroclass A1			EN 13501-1
Total Sulphur		0.27 %	0.55		EN 1744-1
Acid-Soluble Sulfate		0.106 %	0.500		EN 1744-1

Grading (EN 933-1)				
sieve (mm)	mini	% passing	maxi	Declared
0.000		0.0		
0.063		5.9		
0.125		8.8		
0.250		11		
0.500		12		
1.000	0	13	15	
2.000		19		
3.150		73		
4.000		91		
5.000	90	98	100	
6.300		100		

