

AR 0/2-800

Client : Quality Control Argex
 0032/32.50.15.15

lab	Quality Control Argex 0032/32.50.15.15
Aggregate Size	0/2 mm
Certifications	EN 13055 : NL BSB K73820 (1/01/2004)

Essential char. - performance	Minimum	Average	Maximum	Declared	Standard
Particle Shape		Round			EN 13055
Crushing Resistance (T-2x30")		NPD			EN 13055
Loose Bulk Density (+- 15% of declared value)	700	893 kg/m³	900	800	EN 1097-3
Oven-Dried Particle Density (+- 15% of declared value)	1054	1322 kg/m³	1426	1240	EN 1097-6 annex D
Freezing & Thawing Resistance		NPD			EN 1367-7
Los Angeles + Micro Deval (4-6.3)		NPD			EN 1097-1 & 2
Los-Angeles (4-6.3)		NPD			EN 1097-2
Polished Stone Value		NPD			EN 1097-8
Volume Stability		NPD			EN 1367-8
Water Content (from silo)	0.0	0.7 %	15.0		EN 1097-5
Water Absorption 5'	24.18	25.32 %	27.00		EN 1097-6 annex D
Alkali Silica Reactivity		NPD			EN 13055
Chloride		0.005 %	0.010		EN 1744-1
Cleanliness		Pass			EN 1744-1
Release Of Dangerous Substances		NPD			EN 13055
Reaction To Fire		Euroclass A1			EN 13501-1
Total Sulphur		0.35 %	0.55		EN 1744-1
Acid-Soluble Sulfate		0.210 %	0.500		EN 1744-1

Grading (EN 933-1)				
sieve (mm)	mini	% passing	maxi	Declared
0.000		0.0		
0.063		20		
0.125		32		
0.250		42		
0.500		50		
1.000		73		
2.000	90	99	100	
3.150		100		

